



GreenFields MF Elite

60 145 20.6

TECHNICAL DATA

T100304

Type	Synthetic grass carpet for a filled performance system, 5/8" gauge tufted, straight stitch pattern	
Pile content	100% polyethylene yarns, U.V.- resistant, combination of fibres, 20.600/7 dTex: Diamond shape, 15.600/6 dTex, 410 microns Fibrillated tape, 5.000/1 dTex, 110 microns	
Primary backing	Double 100% PP Thiobac, black, U.V.- stabilized, weight ca. 252 gr/m ²	
Secondary backing	Latex compound with a base of styrene-butadiene with drainage holes	
Pile height	60 mm	+/- 5%
Total thickness	62 mm	+/- 5%
Stitch rate per 1m (width)	63	
Stitch rate per 1m (length)	145	+/- 10%
Number of tufts/m ²	9.135	+/- 10%
Number of filaments/m ²	127.890	
Pile weight	2.569 gr/m ²	+/- 10%
Weight primary backing	252 gr/m ²	
Weight secondary backing	1.000 gr/m ²	
Total weight	3.821 gr/m ²	+/- 10%
Roll width	according to seaming plan	+/- 2cm
Roll length	according to seaming plan	
Tuft bind	≥ 40 Newton	
Water permeability	≥ 500mm/h	
Color Fastness	Xenon test : blue-scale>7, grey-scale>4	

Version 1.1, 26/03/2021

COLOUR

Duo tone (Field green/Lime green), White and yellow for line marking.

RECOMMENDED SYSTEM

Carpet needs to be filled with stabilizing and/or performance infill with a max free pile of 18mm
Use of a prefabricated shockpad or insitu layer is optional
For certified system configurations see page 2 or consult your sales representative

INSTALLATION INSTRUCTION:

This product should be stored, handled and installed in accordance with the installation manual, ask our sales representatives for the latest version.



All data shown are typical values based on tests believed to be reliable by TenCate. All technical data provided herein are subject to change without prior notification. TenCate assumes no obligation or liability for the information in this document. No express warranties are given except for any applicable written warranties specifically provided by TenCate. All implied warranties including those of merchantability and fitness for a particular purpose are expressly excluded.



GreenFields MF Elite

60 145 20.6

AVAILABLE SYSTEMS

System name	Performance Infill	Stabilizing Infill	Pad / E-layer / Geo	Tested
GreenFields MF Elite 60 145 20.6 s sbr	SBR 32mm 17,6kg/m ²	Sand 10mm 15kg/m ²	--	A B D
GreenFields MF Elite 60 145 20.6 s sbr PE12.7	SBR 20mm 11kg/m ²	Sand 20mm 30kg/m ²	HP XC 070 012	A B C D
GreenFields MF Elite 60 145 20.6 s sbr PE12.9	SBR 20mm 11kg/m ²	Sand 20mm 30kg/m ²	HP XC 090 012	A B C D

Version 1.1, 26/03/2021

SYMBOLS EXPLAINED

- A** FIFA Quality Programme for Football Turf, Handbook of Requirements October 2015 Edition (Quality)
- B** FIFA Quality Programme for Football Turf, Handbook of Requirements October 2015 Edition (Quality Pro)
- C** The International Rugby Board : Regulation 22, standard relating to the use of artificial playing surfaces.
- D** European standard EN 15330-1, Surfaces for sports areas.
- E** The International Hockey Federation (FIH) "Handbook of performance requirements for synthetic turf hockey pitches"

All data shown are typical values based on tests believed to be reliable by TenCate. All technical data provided herein are subject to change without prior notification. TenCate assumes no obligation or liability for the information in this document. No express warranties are given except for any applicable written warranties specifically provided by TenCate. All implied warranties including those of merchantability and fitness for a particular purpose are expressly excluded.